

**COMPRESSIBILITY OF CLEARCO
PURE SILICONE 20CST**

TEMPERATURE		COMPRESSIBILITY	COMPRESSIBILITY
<u>°F</u>	<u>°C</u>	<u>AT 1200 PSI</u>	<u>AT 800 PSI</u>
77	25	.85%	.57%
150	66	1.00%	.68%
200	93	1.23%	.83%
250	121	1.53%	1.05%
300	149	1.84%	1.25%
350	177	2.11%	1.45%
400	204	2.41%	1.67%
450	232	2.68%	1.86%
500	260	2.89%	2.07%
600	316	3.60%	2.50%